

Conversion Rates used by Oneida County

<i>SPECIES</i>	<i>GREEN WEIGHT</i>		
	<u>lb/cd</u>	<u>Tons/cd</u>	<u>Tons/mbf</u>
Ash	4600	2.30	5.06
Aspen	4500	2.25	4.95
Balsam Fir	4250	2.13	5.20
Basswood	3850	1.93	4.25
Birch, White	4800	2.40	5.28
Birch, Yellow	5350	2.68	5.90
Cedar .	3150	1.58	3.86
Hemlock	4800	2.40	5.86
Maple, Hard (sugar)	5100	2.55	5.61
Maple, Red (Soft)	4550	2.28	5.02
Mixed Hardwood	4900	2.45	5.39
Oak, Red	5500	2.75	6.05
Pine, Jack	4250	2.13	5.20
Pine, Red	4500	2.25	5.49
Pine, White	4200	2.10	5.13
Spruce	4000	2.00	4.88
Tamarack	4650	2.33	5.69